



# Specialty Certificate S2 & 3 Evaluation Report

For HP Indigo



Supplier Contact Information	
Supplier Name	Convertible Solutions
Supplier Address	3500 Snyder Ave., Sedalia, MO, 65301
Supplier Country	United States
Product Name	MultiLoft Kraft Sheet (white ink certified)
Product Category	Paper
Grammage (gsm)/Basis weight (#)	270 gsm
Microns/Caliper	14 Pts
Certification Number	RI7500-19-5746
Certification Center	RIT
Date of Evaluation	04/12/2019
Evaluated on	HP 7500
Certified for	7500, 5500, 5600 multi-shot, 7000, 7600, 7800, 7900, 10000 & 12000
Evaluation Process	Specialty Media

### Certification Validity

This substrate is certified for the next two years from the date of evaluation, provided there is no change to the substrate properties or production processes. At the end of two years from the original evaluation date, if there have been no changes in paper properties or production processes, the certification can be extended for another two years. After four years from the original certification date, a new certification is required.

Evaluation	Measure	Result	Grade (stars)	Comments
Runability			★★★	Front Side Only
Simplex	Number of Jams	0		
Duplex	Number of Jams	0		
Fixing				
Peeling	100% K in 4 color mode, % ink remaining			Delamination
	400% YMCK 100% each color, Visual Damage			
Blanket Compatibility			★★★	
White Ink Recommended		Yes		
Color Registration	CPR quality job	Pass		
Evaluation Result		Pass		

Comment Detail:

**Delamination** - Assumed value is 3 stars. During the peel test, the ink adhered sufficiently to the paper to cause tearing. No data can be obtained from this peel test.

**Front Side Only** - Substrate is a simplex product and only the front side is certified.

The substrate certification procedure incorporates several processes. This checks for:

**Runability:**

The ability of the substrate to run smoothly through the press in various print modes.

**Fixing:**

Ink-substrate interaction as determined by the degree of ink adhesion to the substrate for standard applications as measured in a tape peel test of the image.

**Blanket-substrate interaction as determined by:**

- 1) Ink-transferability, which is the quality of ink transfer from the blanket to the substrate as reflected in highlight dots, thin lines, heavy images and image edge integrity;
- 2) 'Blanket Memory' effects, reflected in gloss or density differences between solids and background areas of the previously printed image; and
- 3) Number of cleaner pages, in which blankets are routinely maintained by performing a self cleaning procedure ("cleaner pages") used to refresh the blanket's release layer.

**Color registration (CPR):**

The ability of the substrate to be printed with acceptable color-to-color registration in the four color process. Synthetic materials are generally more sensitive to CPR issues.

**Star Rating**

- ☆☆☆ Best performing substrate: no blanket memories or very minor memories.
- ☆☆ Recommended substrate: some print cleaners may be needed; slight memories may be seen up to 1.2K impression.
- ☆ Good substrate: print cleaners generally required; some memories may be seen by 1.2K impressions.

		☆☆☆	☆☆	☆
	Measurement	Best-performing substrate	Recommended substrate	Good substrate
Transport	Runnability	No jam and minor issues	1 jam or minor issues	1 jam and minor issues
Fixing	Peeling: 100% K, at 10 minutes	Visually NO damage (ignoring gloss changes)	>90%	>80% at one hour
	Peeling: 400% YMCK, 100% of each color at 10 minutes	Visually NO damage (ignoring gloss changes)	Any damage (visually)	Any damage (visually)
Blanket Compatibility	Cleaner sheets clean after 1.2 K	1st cleaner sheet is clean	3rd cleaner sheet is clean	5th cleaner sheet is clean
Color registration (CPR)	CPR quality job	Pass/Fail		

The specialty test is a shorter test compared to the standard certification procedure, and is intended for media where low print volumes are expected. In addition to runnability, fixing and blanket compatibility, selected Print Quality parameters such as Color Plane. Registration (CPR) are also evaluated. For certain substrates, particularly synthetics, special press procedures may need to be applied to obtain acceptable CPR.

HP Indigo customers must test per their specific application needs and determine if the media meets customer requirements.

